

# S2000A

## 1K WASHPRIMER LIGHTGREY



### DESCRIPTION

S2000/S2000A 1K Wash Primer is an acid primer that's part of the compact Syrox refinish system. It's formulated specifically for use on bare metal and provides very good anti-corrosion protection. The spray can is suitable for smaller repairs and sand-through areas.

### SYROX REFINISH SYSTEM



### PRODUCT LIST

- S2000A 1K WASHPRIMER LIGHTGREY



### FEATURES

- Suitable for use below SYROX S3020 and S3060 Sanding Surfacers.
- Provides excellent adhesion.
- Zinc chromate free.
- Corrosion Protection.
- Ready for use spray can.

# TECHNICAL DATA SHEET

## S2000A

### 1K WASHPRIMER LIGHTGREY



#### Product preparation - application STANDARD

	It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.	
	Bare steel sanded and cleaned Galvanised steel or aluminium sanded and cleaned Surfaces pretreated with 2K polyester products and then finely sanded and cleaned. Old or original paintwork well sanded and cleaned. OEM Primer (e-coat), sanded and cleaned	
	Shake before use. (for at least 2 minutes) Make a spray test after shaking.	
	Not applicable	
	1 - 2 coats	with intermediate flash-off: 5 min - 10 min final flash-off: 10 min - 15 min
	S3110, S3140 & S3170 Sanding Surfacers Plus	

VOC compliant	2004/42/IIB(e)(840) 660: The EU limit value for this product (product category: IIB(e)) in ready to use form is maximum 840 g/l of VOC. The VOC content of this product in ready to use form is maximum 660 g/l.
---------------	--

# TECHNICAL DATA SHEET

## S2000A

### 1K WASHPRIMER LIGHTGREY




#### Products

S2000A 1K WASHPRIMER LIGHTGREY



10 - 20 µm



After use, hold aerosol can upside down and spray briefly to clean nozzle.

#### Remarks

- Material has to be at room temperature (18-25°C) before use.
- Application distance to the substrate should be 15 until 25 cm.
- Owing to the wide variety of metal alloys and manufacturing processes, it is essential to carry out a preliminary test on the respective substrate to ensure that the pretreatment is sufficient to guarantee perfect adhesion.
- Not suitable for application on thermoplastic paintwork.
- Do not recoat with polyester-, epoxy- or waterborne products.

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Syrox product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Syrox product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.